



	Solid content (%)	Viscosity (mPa.s)	pH	MFFT (°C)	Key Features
Wantipro 0612	43	10-200	7-9	37	General purpose emulsion, fast drying and good hardness as well as water resistant
Wantipro 0613	45	10-300	7-9	26	General purpose emulsion, lower coalescent demand, fast drying, corrosion and water resistant
Wantipro 0616	40	10-300	7-9	48	Excellent durability and water resistance (e.g. white spots) together with wide application window
Wantipro 0618	50	10-500	7-9	17	General purpose emulsion, lowest coalescent demand, fast drying, corrosion and water resistant
Wantipro 0620	45	10-200	7-9	55	General purpose emulsion, extreme fast drying & hardness build-up. Very suitable to enhance acrylic, urethane and alkyd emulsions properties.
Wantipro 0626	48	100-1500	7-9	37	Emulsion with balanced properties to suit DTM application with respect to corrosion and water resistance.
Crysol® 6319	40	10-200	8-10	>90	Excellent adhesion to a variety of plastic substrates (e.g. PC, PC+ABS, ABS, PS). Good alcohol resistant.
Lacper 4600	43	10-200	7-9	36	Emulsion with broad adhesion profile, especially for aged coatings and very good pigment dispersing properties
Lacper 4316	40	10-200	7-9	60	Hard emulsion for fast drying wood primers with excellent sanding properties.
Arcshol 8119	48	100-1200	7-9	28	Emulsion for cost efficient wall paints with excellent scrub resistance
Arcshol 8316	55	500-1500	7-9	<0	Emulsion for waterproof coating having excellent cement compatibility